

PE-UHMW ELS
TECHNICAL DATA SHEET

FULL NAME: CONDUCTIVE ULTRA-HIGH MOLECULAR WEIGHT POLYETHYLENE

PROPERTIES	TEST METHOD	UNIT	BLACK
DESCRIPTION		-	PE-UHMW ELS
SPECIFIC GRAVITY	DIN EN ISO 1183-1	G/CM3	≥ 0,93
MEAN MOLECULAR WEIGHT	VISCOMETRY ANALYSIS	MIO. G/MOL	~ 5-6
WATER ABSORPTION AT 23° C	DIN EN ISO 62	%	< 0,01

**MECHANICAL PROPERTIES AT STANDARD ATMOSPHERE –
DIN EN ISO 291 – 23/50**

ABRASION (SAND SLURRY TEST)	DIN EN ISO 15527	%	100
YIELD STRESS	DIN EN ISO 527-1	MPA	≥ 17
MODULUS OF ELASTICITY (TENSILE)	DIN EN ISO 527-1	MPA	> 700
IMPACT STRENGTH – CHARPY	DIN EN ISO 179-1	KJ/M2	≥ 170
SHORE – HARDNESS D	DIN EN ISO 868	-	60 – 65

THERMAL PROPERTIES

THERMAL CONDUCTIVITY AT 23°C	ISO 52612	W / M X K	0,40
COEFFICIENT OF EXPANSION (BETWEEN 23°C – 80°C)	ISO 1135-2	M / K X M	20x10 ⁻⁵
OPERATING TEMPERATURE	SHORT TERM LONG TERM	°C °C	~ 100 ~ -200 / +80
MELTING TEMPERATURE	ISO 11357-3	°C	135
FLAMMABILITY ACC. TO UL94 – TEST THICKNESS 3/6 MM	-	-	HB

**ELECTRICAL PROPERTIES AT STANDARD ATMOSPHERE –
DIN EN ISO 291 – 23/50**

DIELECTRIC STRENGTH	IEC 60243-1	KV/MM	-
INSULATION RESISTANCE	DIN EN 62631 -3-1	Ω X CM	< 10 ⁴
SURFACE RESISTANCE	DIN EN 62631 -3-1	Ω	< 10 ⁴

REV.	DATE	DESCRIPTION	MODIFIED PARAGRAPHS	WRITTEN BY	APPROVED BY
01	12/2020	LAYOUT UPDATE	//	602.18	602.18

D.H. LAMINA S.R.L.

Via Santellone, 29/A • 25080 Molinetto di Mazzano (BS) • Italy
Tel. +39 (0) 30 21 20 448 • Fax +39 (0) 26 20 813
Capitale Sociale € 46.800,00 Interamente versato
C.F. e Nr. Iscr. Registro Imprese 01685670174
P.I. IT01685670174 • REA BS-262362
PEC: dhlamina@pec.it • dhlamina@dhlamina.it • www.dhlamina.it

PE-UHMW ELS

TECHNICAL DATA SHEET



THIS DATASHEET AND ALL PROPRIETIES INDICATED COME DIRECTLY FROM THE PRODUCER'S STUDIES AND TESTS. D.H. LAMINA S.R.L. DOES NOT PRODUCE THE MATERIAL.

THE CONTENTS OF THIS DATASHEETS ARE MEANT TO GIVE AN OVERVIEW OF THE PRODUCT'S PROPRIETIES. IT REFLECTS OUR CURRENT KNOWLEDGE AND MAY NOT BE COMPLETE. THE VALUES SHOULD BE TAKEN AS GUIDE VALUES BECAUSE THEY ARE DEPENDENT ON SURROUNDING CONDITIONS AND MACHINING METHODS. THE VALUES ARE IN NO WAY A LEGALLY BINDING ASSURANCE OF THE PRODUCT'S PROPRIETIES OR ITS SUITABILITY FOR USE IN A SPECIFIC APPLICATION. ALL STATED VALUES ARE AVERAGE ESTABLISHED FROM MANY INDIVIDUAL TESTS. FOR SPECIFIC APPLICATIONS, WE RECOMMEND DETERMINING SUITABILITY BY MEANS A TRIAL.

D.H. LAMINA S.R.L.

Via Santellone, 29/A • 25080 Molinetto di Mazzano (BS) • Italy
Tel. +39 (0) 30 21 20 448 • Fax +39 (0) 26 20 813
Capitale Sociale € 46.800,00 Interamente versato
C.F. e Nr. Iscr. Registro Imprese 01685670174
P.I. IT01685670174 • REA BS-262362
PEC: dhlamina@pec.it • dhlamina@dhlamina.it • www.dhlamina.it